



IMM

Istituto Meccanica dei Materiali SA
Via al Molino
CH - 6916 Grancia

Cava Boschetto, Bettazza Graniti SA, CH - 6675 Cevio

05

SN EN 1341

Slabs of natural stone for external paving

Biotitic paragneiss

Water absorption at atmospheric pressure	0.3 %
Flexural strength under concentrated load	18.6 MPa
Flexural strength after freeze/thaw cycles	17.5 MPa
Unpolished slip resistance (USRV)	85
Abrasion resistance	19 mm